

AN AMERICAN NATIONAL STANDARD

Tool Life Testing With Single-Point Turning Tools

ANSI/ASME B94.55M - 1985

[REVISION OF ANSI B94.34-1946 (R1971) AND B94.36-1956 (R1971)]

REAFFIRMED 1995

FOR CURRENT COMMITTEE PERSONNEL
PLEASE SEE ASME MANUAL AS-11

SPONSORED AND PUBLISHED BY

THE AMERICAN SOCIETY OF MECHANICAL ENGINEERS

United Engineering Center 345 East 47th Street New York, N. Y. 10017

Date of Issuance: April 15, 1986

This Standard will be revised when the Society approves the issuance of a new edition. There will be no addenda or written interpretations of the requirements of this Standard issued to this Edition.

This code or standard was developed under procedures accredited as meeting the criteria for American National Standards. The Consensus Committee that approved the code or standard was balanced to assure that individuals from competent and concerned interests have had an opportunity to participate. The proposed code or standard was made available for public review and comment which provides an opportunity for additional public input from industry, academia, regulatory agencies, and the public-at-large.

ASME does not "approve," "rate," or "endorse" any item, construction, proprietary device, or activity.

ASME does not take any position with respect to the validity of any patent rights asserted in connection with any items mentioned in this document, and does not undertake to insure anyone utilizing a standard against liability for infringement of any applicable Letters Patent, nor assume any such liability. Users of a code or standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, is entirely their own responsibility.

Participation by federal agency representative(s) or person(s) affiliated with industry is not to be interpreted as government or industry endorsement of this code or standard.

ASME accepts responsibility for only those interpretations issued in accordance with governing ASME procedures and policies which preclude the issuance of interpretations by individual volunteers.

No part of this document may be reproduced in any form,
in an electronic retrieval system or otherwise,
without the prior written permission of the publisher.

Copyright © 1986 by
THE AMERICAN SOCIETY OF MECHANICAL ENGINEERS
All Rights Reserved
Printed in U.S.A.

FOREWORD

(This Foreword is not part of ANSI/ASME B94.55M-1985.)

This Standard is a slightly modified version of ISO 3685-1977, Tool Life Testing With Single-Point Turning Tools. Only several small changes have been made, such as replacing referenced ISO materials specifications with ASTM and ANSI specifications. It was felt that U.S. users of the Standard would be more familiar with the ASTM and ANSI specifications and have easier access to them.

Following approval by the B94 Standards Committee and ASME, this Standard was submitted to ANSI and approved as an American National Standard on November 27, 1985.

ASME STANDARDS COMMITTEE B94
Standardization of Cutting Tools, Holders, Drivers, and Bushings

(The following is the roster of the Committee at the time of the approval of the Standard.)

OFFICERS

E.J. Czopor, *Chairman*
W.R. Daisak, *Secretary*

COMMITTEE PERSONNEL

AMERICAN SOCIETY OF MECHANICAL ENGINEERS, THE

M.E. Merchant, Metcut Research Associates, Inc., Cincinnati, Ohio
G.F. Wilson, *Alternate*, General Electric Co., Worthington, Ohio

CUTTING TOOL MANUFACTURERS OF AMERICA

E.J. Czopor, Falcon Tool Co., Warren, Michigan
C.W. Jatho, *Alternate*, Cutting Tool Manufacturers of America, Birmingham, Michigan

GENERAL SERVICES ADMINISTRATION

W.R. Wacker, General Services Administration, Washington, DC

HACK AND BAND SAW MANUFACTURERS ASSOCIATION OF AMERICA

R. Schrade, Clemson Brothers, Inc., Middletown, New York
C.M. Stockinger, *Alternate*, Hack and Band Saw Manufacturers Association, Cleveland, Ohio

METAL CUTTING TOOL INSTITUTE

W.A. Wagner, Cleveland Twist Drill Co., Cleveland, Ohio
J.G. Thimmig, *Alternate*, Metal Cutting Tool Institute, Cleveland, Ohio

NATIONAL MACHINE TOOL BUILDERS ASSOCIATION

J.J. Robinson, Valeron Corp., Troy, Michigan
A.M. Bratkovich, *Alternate*, National Machine Tool Builders Association, McLean, Virginia

SOCIETY OF MANUFACTURING ENGINEERS

G.L. Spencer, Ford Motor Co., Detroit, Michigan

UNITED STATES DEPARTMENT OF THE ARMY

D.L. York, Liaison, Material Readiness Command, Rock Island, Illinois

INDIVIDUAL MEMBERS

A. Ashburn, *American Machinist*, New York, New York
H. Cooper, Water Technology, Inc., Troy, Michigan
R.T. Koblesky, Ingersoll Cutting Tool Co., Rockford, Illinois
J.A. Lang, Dayton Progress Corp., Dayton, Ohio
L. Storrer, Mohawk Tools, Inc., Montpelier, Ohio

PERSONNEL OF TECHNICAL COMMITTEE 4 – LIFE TESTING WITH SINGLE-POINT TOOLS

M.E. Merchant, *Chairman*, Metcut Research Associates, Inc., Cincinnati, Ohio

R.M. Byrne, Trade Association Management, Inc., Tarrytown, New York

D.D. Jackson, Valeron Corp., Warren, Michigan

J. Johnston, General Electric Co., Warren, Michigan

J.F. Kahles, Metcut Research Associates, Cincinnati, Ohio

J.D. Knox, Vermont American Corp., Louisville, Kentucky

CONTENTS

Foreword	iii
Standards Committee Roster	v
0 Introduction	1
1 Scope and Field of Application	1
2 References	1
3 Workpiece	2
4 Tool	3
5 Cutting Fluid	7
6 Cutting Conditions	7
7 Tool Life Criteria and Tool Wear Measurements	10
8 Equipment	12
9 Tool Life Test Procedure	12
10 Recording and Reporting Results	12
Figures	
1 Tool Angles	4
2 Details of Rounded Corner	5
3 Tolerances on Squareness of Insert and Toolholder Location	6
4 Insert Overhang and Chipbreaker	6
5 Regrinding Tool After Testing	7
6 Limits of Cutting Conditions	9
7 Broken v - T Curve, Combined Flank and Crater Wear	9
8 Some Types of Wear on Turning Tools	11
9 Development of Flank Wear for Different Cutting Speeds	13
10 Development of Crater Depth for Different Cutting Speeds	13
11 v - T Curve for $VB_B = 0.3$ mm	14
12 v - T Curve for $KT = 0.18$ mm	14
13 Number of Workpieces Produced as a Function of Spindle Speed	14
Tables	
1 Standard Tool Angles, deg.	4
2 Standard Cutting Conditions	7
3 Limits of Other Cutting Conditions	8
4 Geometric Series of Preferred Numbers for Cutting Speeds (m/min)	8
Appendices	
A General Information	17
B Grinding of High-Speed Steel	19
C Tool Wear and Tool Life Criteria	23
D Data Sheets	27

E	Preliminary Tool Life Test	31
F	Evaluation of Tool Life Data	33
G	Chip Forms	49

Figures

14	21
15	21
16	33
17	Lines Fitted "By Eye"	39
18	Lines With Confidence Interval Fitted by Calculation	40

Tables

5	Grinding Recommendations	20
6	Computation Schedule for Calculation of Regression Line $y = a + k(x - \bar{x})$	41
7	Computation Schedule for Assessment of Dispersion and Significance	42
8	Computation Schedule for Calculation of Confidence Intervals	43
9	Example	44
10	Example	45
11	Example	46
12	<i>t</i> -Distribution for 95% Confidence Level	47

AN AMERICAN NATIONAL STANDARD

TOOL LIFE TESTING WITH SINGLE-POINT TURNING TOOLS

0 INTRODUCTION

Tool life testing has been carried out for at least 75 years, in tremendously increasing volume, but under a variety of cutting conditions and methods having little in common with each other. Thus, a need exists for standardization of tool life testing conditions applicable not only in laboratories but also in production plants.

The test conditions have been specified in such a way that the different factors which affect the results of tool life testing will all be under a reasonable and practical degree of control.

This Standard has been so framed that it can be directly applied to industrial testing and in research. For research purposes, however, this Standard should be considered to be only a minimum set of conditions, since greater attention may have to be given to the factors which affect the variability of the tool life values. Although the test parameters are standardized, any one or more of them may become variables in any given test when they are the quantities being examined.

The limits of the specification of the reference materials are left rather wide for practical reasons. It should be understood that results may vary from batch to batch. If reproducibility is essential, special requirements should be discussed with the supplier of the work material.

The specifications for test conditions given in this Standard are primarily suited to testing on steel and cast iron work materials. However, with suitable modification they can also be made applicable to testing on other materials.

The specifications for test conditions are also mainly applicable to tool life testing in which the tool wears at a conventional rate and in a conventional manner. However, it is evident that they may also be applied to some types of accelerated tool life testing.

If, for some reason, it is necessary to deviate from the specifications given in this Standard, this shall be reported in detail.

NOTE: This Standard is not an acceptable test and it is not advisable to use it as such.

1 SCOPE AND FIELD OF APPLICATION

This Standard establishes specifications for the following factors of tool life testing with single-point turning tools: workpiece, tool, cutting fluid, cutting conditions, tool wear and tool life, equipment, test procedures, recording and reporting and presentation of results.

Further general information is given in Appendix A.

2 REFERENCES

The latest issues of the following documents form a part of this Standard to the extent specified herein.

American Society for Testing and Materials

ASTM A 159-83, Standard Specification for Automotive Gray Iron Castings (Grade G 3000)

ASTM A 576-81, Standard Specification for Steel Bars, Carbon, Hot-Wrought, Special Quality (Grade G 10450)

ASTM E 18-79, Standard Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E 92-82, Standard Test Method for Vickers Hardness of Metallic Materials

ASTM E 112-82, Standard Methods for Determining Average Grain Size