

Australian Standard™

**Radiography of metals—Image quality  
indicators (IQI) and recommendations  
for their use**



This Australian Standard was prepared by Committee MT-007, Non-destructive Testing of Metals and Materials. It was approved on behalf of the Council of Standards Australia on 19 April 2006.  
This Standard was published on 18 May 2006.

---

The following are represented on Committee MT-007:

Australian Railway Association  
Australian Aerospace Non-Destructive Testing Committee  
Australian Industry Group  
Australian Institute for Non-Destructive Testing  
Australian Nuclear Science & Technology Organisation  
Australian Pipeline Industry Association  
Bureau of Steel Manufacturers of Australia  
Engineers Australia  
National Association of Testing Authorities Australia  
New Zealand Non-Destructive Testing Association  
TestSafe Australia  
Victorian WorkCover Authority  
Welding Technology Institute of Australia

---

### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.org.au](mailto:mail@standards.org.au), or write to the Chief Executive, Standards Australia, GPO Box 476, Sydney, NSW 2001.

---

*This Standard was issued in draft form for comment as DR 05544.*

STANDARDS AUSTRALIA

---

RECONFIRMATION

OF

AS 2314—2006

**Radiography of metals—Image quality indicators (IQI) and recommendations for their use**

---

**RECONFIRMATION NOTICE**

Technical Committee MT-007 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 22 November 2016.

The following are represented on Technical Committee MT-007:

Australasian Thermographers Association  
Australian Aerospace Non-Destructive Testing Committee  
Australian Institute for Non-Destructive Testing  
Australian Nuclear Science & Technology Organisation  
AUSTROADS  
Bureau of Steel Manufacturers of Australia  
Engineers Australia  
Institute of Electrical Inspectors  
National Association of Testing Authorities Australia  
New Zealand Non-Destructive Testing Association  
TestSafe Australia  
Welding Technology Institute of Australia  
WorkSafe Victoria

## NOTES

Australian Standard™

**Radiography of metals—Image quality indicators (IQI) and recommendations for their use**

Originated as AS B262—1968.  
Previous edition AS 2177.2—1982.  
Revised and redesignated as AS 2314—2006.

**COPYRIGHT**

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia, GPO Box 476, Sydney, NSW 2001, Australia

ISBN 0 7337 7408 3

## PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee MT-007, Non-destructive Testing of Metals and Materials. After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

This Standard supersedes AS 2177.2—1982, *Radiography of welded butt joints in metal, Part 2: Image quality indicators (IQI) and recommendations for their use*.

The objective of this Standard is to specify the procedure for determining the image quality indicators for X-ray or gamma-ray radiography of metals.

In the preparation of this Standard cognizance was taken of the following Standards:

EN

- 462 Non-destructive testing—Image quality of radiographs
- 462-1 Part 1: Image quality indicators (wire type), determination of image quality value
- 462-2 Part 2: Image quality indicators (step/hole type), determination of image quality value

The term ‘informative’ has been used in this Standard to define the application of the appendix to which it applies. An ‘informative’ appendix is only for information and guidance.

## CONTENTS

	<i>Page</i>
FOREWORD.....	4
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE .....	5
1.2 REFERENCED DOCUMENTS .....	5
1.3 DEFINITIONS .....	6
SECTION 2 IQI CHARACTERISTICS	
2.1 WIRE IQI (W).....	7
2.2 STEP/HOLE IQI (SH).....	9
2.3 PLAQUE/HOLE IQI (PH).....	11
SECTION 3 IMAGE QUALITY INDICATORS AND THEIR USE	
3.1 SELECTION OF IQI.....	14
3.2 LOCATION OF IQI .....	14
3.3 ASSESSMENT OF IQI PERCENT SENSITIVITY .....	14
3.4 EQUIVALENT SENSITIVITY .....	15
APPENDICES	
A WIRE IQI SENSITIVITIES FOR STEEL .....	19
B MATERIALS OF CONSTRUCTION OF IMAGE QUALITY INDICATORS .....	25
C NOMOGRAPH FOR DETERMINING IQI SENSITIVITY FOR PLAQUE/HOLE OR STEP HOLE METHODS .....	27
D WIRE IQI MATERIALS .....	29
E STEP/HOLE IQI MATERIALS .....	30

## FOREWORD

The elements, wires or holes, of image quality indicators (IQI) are used to indicate the sensitivity of the radiographic process. The image quality is characterized by the smallest element of a series of wires, or by the smallest of a series of holes in plates of different thicknesses, the image of which can be discerned visually when a film is placed on an illuminated screen of the required brightness as specified in AS 2177.

In this Standard the following parameters are considered when using IQIs:

- (a) The number value of the IQI is dependent on the material thickness.
- (b) IQI sensitivity required is influenced by the radiographic test method used.
- (c) The percentage sensitivity will not be the same for different metal thickness.
- (d) The elements of the visibility of an IQI is subjective and it depends upon the following factors:
  - (i) Visual acuity.
  - (ii) Viewing conditions.
  - (iii) Experience and ability in assessing IQI images.
  - (iv) Radiographic contrast.

Other factors which can influence IQI are:

- (A) Tube voltage or type of radiography
- (B) Source-to-film and object-to-film distances.
- (C) Film type and screen material and thickness.
- (D) Film density and processing.
- (E) Location of IQI.

## STANDARDS AUSTRALIA

### Australian Standard

## Radiography of metals—Image quality indicators (IQI) and recommendations for their use

### SECTION 1 SCOPE AND GENERAL

#### 1.1 SCOPE

This Standard specifies requirements for the following three types of image quality indicators (IQI) used in X-ray or gamma-ray radiographic examination of metals and includes recommendations for their use:

- (a) Wire IQI (W).
- (b) Step/hole IQI (SH).
- (c) Plaque/hole IQI (PH).

#### NOTES:

- 1 Advice and recommendations on wire IQI sensitivities are contained in Appendix A.
- 2 Guidance and general information on materials of construction of IQIs, which should assist the users of this Standard, is contained in Appendix B.

#### 1.2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard.

#### AS

- 1929 Non-Destructive testing—Glossary of terms
- 2177 Non-destructive testing—Radiography of welded butt joints in metal
- 3507 Non-destructive testing
- 3507.1 Part 1: Guide to radiography for ferrous castings

#### ISO

- 17 Guide to the use of preferred numbers and of series of preferred numbers
- 497 Guide to the choice of series of preferred numbers and of series containing more rounded values of preferred numbers

#### EN

- 462 Non-destructive testing—Image quality of radiographs
- 462-1 Part 1: Image quality indicators (wire type). Determination of image quality value
- 462-2 Part 2: Image quality indicators (step/hole type). Determination of image quality value

#### ASTM

- B139 Standard specification for phosphor bronze rod, bar and shapes
- B150 Standard specification for aluminium bronze rod, bar and shapes
- B151 Standard specification for copper-nickel-zinc alloy (nickel silver) and copper-nickel rod and bar
- B164 Standard specification for nickel-copper alloy rod, bar, and wire